

## ALD Operation Instructions

- 1) Log In by clicking on System and select PASSWORD.
- 2) Enter Name and Password and click OK.
- 3) Click on SYSTEM, select Pumping.
- 4) On the left side of the screen, click on STOP then click on VENT.
- 5) Load wafer. Use carrier wafer for chips and wafers smaller than 5"
- 6) On the left side of the screen, click on STOP then click on EVACUATE.
- 7) Screen will prompt to enter wafer name for run. Click on ENTER.
- 8) Click on PROCESS, select RECIPES.
- 9) Click on LOAD, screen will prompt to overwrite recipe, select YES.
- 10) Select desired recipe.
- 11) Click on step named REPEAT (#) and select REPEAT STEP from selection.
- 12) Enter desired number of repeat steps based on deposition rate and final thickness desired and click on OK.
- 13) Click on SYSTEM, select Pumping, Verify loadlock Penning is  $< 2.0 \times 10^{-5}$  torr.
- 14) Click on PROCESS, select RECIPES.
- 15) Click on RUN. Wafer will be loaded into the process chamber, the recipe will run, wafer will be unloaded from the process chamber when the recipe is finished.
- 16) When recipe is complete Screen will prompt Accept Yellow Flag. Click on ACCEPT.
- 17) WAIT for the wafer to be unloaded from the process chamber.
- 18) Click on SYSTEM, select Pumping
- 19) On the left side of the screen, click on STOP then click on VENT.
- 20) Remove wafer from loadlock, close lid.
- 21) On the left side of the screen, click on STOP then click on EVACUATE.
- 22) Finished

Basic Recipes for ALD. Change cycle numbers only.

Material	Sub Temp (C)	RecipeName	Rate (A/Cycle)	Index at 633nm
Al <sub>2</sub> O <sub>3</sub>	100	Al <sub>2</sub> O <sub>3</sub> 100	1.41	1.585
Al <sub>2</sub> O <sub>3</sub>	300	Al <sub>2</sub> O <sub>3</sub> Plasma300C	1.15	1.617
AlN	300	AlN 300C	0.65	1.75
Al <sub>2</sub> O <sub>3</sub>	300	Al <sub>2</sub> O <sub>3</sub> Water300CSaturated	1.20	1.66
HfO <sub>2</sub>	100	HfO <sub>2</sub> 100	1.26	1.879
HfO <sub>2</sub>	300	HfO <sub>2</sub> 300	1.13	2.032
ZrO <sub>2</sub>	300	ZrO <sub>2</sub> 300	1.32	2.071
SiO <sub>2</sub>	100	SiO <sub>2</sub> 100	1.12	1.423
SiO <sub>2</sub>	300	SiO <sub>2</sub> 300	0.85	1.445

Please be aware of the thermal properties of your material.

Do NOT use any oil.

Note all usage in the logbook.