

Date	User	Film	Recipe	Dep.time	Thickness	JAW EC-400 (Woolam S. E.)		Avg Index	Index+1%	Index -1%	Avg.dep. rate				HF e.r.	Stress	Avg. Stress	Avg+30%	Avg-30%	LPD (light point defects)		Comment	Mike Silva
						Index @ 632.8nm	Index @ 1550nm				(nm/min)	(nm/min)	(nm/min)	(nm/min)						(nm/min)	(nm/min)		
TiO2																							
01/09/14	Bijja	TiO2	Bijja_1_TiO2_dep	900	204.98	2.327	2.378	2.346	2.369	2.322	1.37	1.38	1.51	1.24	6.61	-532.49	-441.90	-574.47	-309.33	157	381	Not many particles	
01/31/14	Bijja	TiO2	Bijja_1_TiO2_dep	900	217.77	2.351	2.378	2.346	2.369	2.322	1.45	1.38	1.51	1.24	10.43	-492.48	-441.90	-574.47	-309.33			LPD not done	
03/19/14	Bijja	TiO2	Bijja_1_TiO2_dep	900	196.94	2.359	2.314	2.346	2.369	2.322	1.31	1.38	1.51	1.24	To do!	-300.72	-441.90	-574.47	-309.33	103	325	Not many particles	

Avg. Thickness	206.56	Avg. Index	2.346	Avg. Dep. Rate	1.38	Avg HF e.r.	-441.90
		Avg+1%	2.369	Avg+10%	1.51	Avg+30%	-574.47
		Avg-1%	2.322	Avg-10%	1.24	Avg-30%	-309.33

